

DH-60M Series 295-315W

Monocrystalline Silicon Module





Advanced processing techniques realize great module efficiency to a maximum of 19.36%, steady power output guaranteed



0~+5W Positive tolerance delivers higher output reliability



Excellent performance even under low-light settings, such as dawn, dusk and cloudy day



Advanced cell technology and qualified materials lead to high resistance to PID




Excellent mechanical load resistance: wind loads (2400Pa) & snow loads (5400Pa)



Reliable quality leads to a better sustainability even in harsh environment like desert, farm and coastline

LINEAR PERFORMANCE WARRANTY























ELECTRICAL PROPERTIES STC*	DH-60M-295	DH-60M-300	DH-60M-305	DH-60M-310	DH-60M-315
Peak Power (Pmax W)	295	300	305	310	315
MPP Voltage (Vmp V)	32.60	32.90	33.20	33.40	33.70
MPP Current (Imp A)	9.05	9.12	9.20	9.28	9.37
Open Circuit Voltage (Voc V)	39.50	39.70	39.90	40.10	40.30
Short Circuit Current (Isc A)	9.51	9.57	9.63	9.69	9.75
Module Efficiency (%)	18.13	18.44	18.75	19.05	19.36
Power Tolerance			0~+5W		
Operating Temperature	-40°C ~ +85°C				
Maximum System Voltage	1500V (IEC)				
Maximum Series Fuse Rating	15A				
Fire Safety	Class C				

^{*}STC (Standard Test Condition): Irradiance 1000W/m², Cell Temperature 25°C, AM 1.5

ELECTRICAL PROPERTIES NOCT*					
Peak Power (Pmax W)	217	221	225	229	233
MPP Voltage (Vmp V)	30.10	30.30	30.70	31.00	31.20
MPP Current (Imp A)	7.24	7.30	7.34	7.39	7.44
Open Circuit Voltage (Voc V)	36.50	36.70	36.90	37.10	37.30
Short Circuit Current (Isc A)	7.69	7.74	7.79	7.84	7.89

^{*}NOCT (Nominal Operating Cell Temperature): Irradiance 800W/m², Ambient Temperature 20°C, AM 1.5, Wind Speed 1m/s


MECHANICAL PROPERTIES		
Cell Type	Mono Cell (156.75 x 156.75mm)	
Number of Cells	6 x 10 (60pcs)	
Dimension	1640x992x35mm	
Weight	18.0kg	
Front/Rear Glass	3.2mm Tempered Glass	
Frame	Anodized Aluminium Alloy	
Junction Box	IP67, 3 Diodes	
Cable Type	4.0 mm ²	
Length of Cable	1000mm	
Connector	MC4 Compatible	

TEMPERATURE COEFFICIENT	
Temp. Coeff. of Pmax (TK Pmax)	-0.390%/°C
Temp. Coeff. of Voc (TK Voc)	-0.300%/°C
Temp. Coeff. of Isc (TK Isc)	0.05%/°C
NOCT	45±2°C

PACKING MANNER		
Packing Type	20GQ	40HQ
Piece/Pallet	30	30
Pallet/Container	12	28
Piece/Container	360	840


^{*} The specification and key features described in this datasheet may deviate slightly and are not guaranteed. Due to ongoing innovation, R&D enhancement, Dehui Solar reserves the right to make any adjustment to the information described herein at any time without notice. Please always obtain the most recent version of the datasheet which shall be duly incorporated into the binding contract made by the parties governing all transactions related to the purchase and sale of the products described herein.

ENGINEERING DRAWING (unit: mm)




I-V CURVES

Irradiance Dependence of Isc, Voc and Pmax



Temperature Dependence of Isc, Voc and Pmax



Tel: +86 510 8855 9088 Fax: +86 510 8815 6008 Email: sales@dehui-solar.com Germany Office: Sebastian-Kneipp-Str.41 60439 Frankfurt, Germany Vietnam Factory: Dai Dong-Hoan Son Industrial Zone, Bac Ninh Province, Vietnam

